



11) Publication number:

⁻ 0 407 996 A3

(12)

EUROPEAN PATENT APPLICATION

(2) Application number: 90113245.6

2 Date of filing: 11.07.90

(9) Int. Cl.⁵: **B29C 67/20**, B29C 67/22, B29C 67/12, B29C 67/14, B29C 67/18

Priority: 12.07.89 JP 179830/89
 02.10.89 JP 255304/89
 02.10.89 JP 255305/89
 07.12.89 JP 316403/89

② Date of publication of application: 16.01.91 Bulletin 91/03

Designated Contracting States:
DE FR GB

Date of deferred publication of the search report: 02.01.92 Bulletin 92/01

7) Applicant: TEIJIN LIMITED
6-7, Minamihommachi 1-chome Chuo-ku
Osaka(JP)

2 Inventor: Inoue, Masataka
3-1-40, Yamate-cho
Iwakuni-shi, Yamaguchi-ken(JP)
Inventor: Yamamoto, Michio
3-1-40, Yamate-cho
Iwakuni-shi, Yamaguchi-ken(JP)
Inventor: Yamada, Takeyoshi
5-9-1, Muronoki-cho
Iwakuni-shi, Yamaguchi-ken(JP)
Inventor: Kimura, Shigekazu
7-14-19, Marifu-cho
Iwakuni-shi, Yamaguchi-ken(JP)

Representative: Kraus, Walter, Dr. et al Patentanwälte Kraus, Welsert & Partner Thomas-Wimmer-Ring 15 W-8000 München 22(DE)

- Process for the production of composite molded articles.
- Disclosed is a process for the production of an integral composite molded item comprising
 - (i) a surface portion (c) comprising a synthetic resin phase containing a fibrous reinforcing material
 - (ii) a core portion (a) comprising the synthetic resin phase containing bubble-containing particles, and
 - (iii) a separation layer (b) positioned between the surface portion and the core portion,

the process comprising the steps of:

- (a) providing in a substantially sealed mold (1) a separation layer which does not substantially pass therethrough expandable particles or compressed lightweight particles of an elastic material but which is capable of passing a synthetic resin or its precursor that is liquidized at the time of molding;
- (b) providing the synthetic resin or its precursor in the mold;
- (c) arranging a fibrous reinforcing material (3)

between the separation layer and the mold, integrated with the separation layer or separately but associated therewith;

- (d) providing an aggregate of the expandable particles (4) and/or compressed particles of the lightweight elastic material on a side of the separation layer opposite to the side of an inner surface of the mold;
- (e) causing volume expansion of the aggregate by elevation of temperature to thereby expand the expandable particles or relieving compression urged on the compressed lightweight particles to thereby expand the lightweight particles;
- (f) flowing the liquidized synthetic resin or its precursor through the separation layer to spread it over between the separation layer and the mold, and among the expanded particles, or among the particles of the lightweight elastic material, while pressing the separation layer onto the inner surface of the mold as the result of volume expansion in the step (e) above;

- (g) completing formation-solidification or solidification of the synthetic resin to form a surface portion and a core portion; and
- (h) taking out the resulting composite molded item.

The type of the resin and the type of bubble-containing particles may be selected and combined differently.



EUROPEAN SEARCH REPORT

Application Number

EP 90 11 3245

					EP 90 11 324
DOCUMENTS CONSIDERED TO BE RELEVANT					•
Category		ith indication, where appropriate, evant passages		vant Iaim	CLASSIFICATION OF THE APPLICATION (Int. CL5)
х	US-A-4 025 686 (E M ZIC * column 5, line 58 - colum line 18 * *		1,2,4 ine 8 - 19,2 30,3	1-26, B 1 B	29 C 67/20 29 C 67/22 29 C 67/12 29 C 67/14
Α	US-A-4 040 165 (J D MIE * column 2, line 58 - line 66		9 61 **	В	29 C 67/18
Α	EP-A-0 247 708 (EX-CEL * the whole document * *	L-O CORPORATION)	1-5,2	20	
P,A	WORLD PATENTS INDEX TIONS LTD, London, GB A & JP-A-1316236 (TEIJIN) 2	N 90-040135 [06] , DW900			
D,A	EP-A-0 272 359 (M WARE) * the whole document * *				
	-	-			
					TECHNICAL FIELDS SEARCHED (Int. CI.5)
		•		В	29 C
	The present search report has	been drawn up for all claims			
	Place of search The Hague	Date of completion of se 28 October 91	arch	P	Examiner HILPOTT G.R.
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same catagory A: technological background O: non-written disclosure P: intermediate document			E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons 8: member of the same patent family, corresponding document		